

LAMINA NEGRA

CAL.	ESPESOR		KG/M2	KG/PZA				
	MM	PULG		3 X 6	3 X 8	3 X 10	4 X 8	4 X 10
16	1.52	0.059	12.21	20.41	27.21	34.02	36.28	45.35
17	1.37	0.053	10.98	18.37	24.49	30.61	32.65	40.82
18	1.21	0.047	9.76	16.33	21.77	27.21	29.03	36.28
19	1.06	0.041	8.54	14.28	19.05	23.81	25.40	31.75
20	0.91	0.035	7.32	12.24	16.33	20.41	21.77	27.21
21	0.84	0.032	6.71	11.22	14.96	18.71	19.95	24.94
1/32	0.79	0.031	6.37	10.65	14.20	17.75	18.93	23.66
22	0.76	0.029	6.10	10.20	13.60	17.01	18.14	22.68
23	0.68	0.026	5.49	9.18	12.24	15.30	16.32	20.41
24	0.61	0.023	4.88	8.16	10.88	13.60	14.51	18.14
25	0.53	0.020	4.27	7.14	9.52	11.90	12.70	15.87
26	0.45	0.017	3.66	6.12	8.16	10.20	10.88	13.60
27	0.42	0.016	3.35	5.61	7.48	9.35	9.97	12.47
28	0.38	0.014	3.05	5.10	6.80	8.50	9.07	11.34
29	0.34	0.013	2.74	4.59	6.12	7.65	8.16	10.20
30	0.30	0.012	2.44	4.03	5.44	6.80	7.25	9.07
31	0.27	0.010	2.13	3.57	4.70	5.95	6.34	7.93
32	0.24	0.009	1.98	3.31	4.42	5.52	5.89	7.37

ROLADO EN FRÍO

PESOS TEÓRICOS CON UNA VARIACIÓN DE $\pm 5\%$